

# DOF-LITE™ (METRO)

## ITU-T G655E.G656 Single Mode Optical Fiber

### Product Description

DOF-LITE™ (METRO) Single Mode Optical Fiber is a Non-Zero Dispersion Shifted Fiber (NZ-DSF).

### Product Application

DOF-LITE™ (METRO) is ideal for high data-rate, multi-wavelength long haul transmission. It is suitable for transmission in the conventional C-band (1530-1565 nm) and L-band (1565- 1625 nm).

### Product Specifications

Attenuation	≤0.21 dB/km at 1550 nm ≤0.24 dB/km at 1625 nm
Mode field diameter at 1550 nm	9.2 ± 0.5 μm
Cable cutoff wavelength	≤1450 nm
Dispersion at 1460 nm	1.00 to 4.60 ps/nm.km
Dispersion at 1530 nm	3.02 to 8.24 ps/nm.km
Dispersion at 1550 nm	3.60 to 9.28 ps/nm.km
Dispersion at 1565 nm	3.80 to 10.13 ps/nm.km
Dispersion at 1625 nm	4.58 to 13.43 ps/nm.km
PMD Individual Fibre*	≤0.1 ps/√km
PMD LDV	≤0.06 ps/√km
Cladding diameter	125 ± 0.7 μm
Core-clad concentricity error	≤0.5 μm
Cladding non-circularity	≤0.8 %
Coating diameter (uncolored)	242 ± 5 μm
Coating-cladding concentricity error	≤12 μm

\* Individual PMD values may change when cabled

### Mechanical Characteristics

Proof Test Levels	≥100 kpsi (0.7 GN/m <sup>2</sup> ). This is equivalent to 1% strain
Coating strip force (Force to mechanically strip the dual coating)	≥1.3 N (0.3 lbf) and ≤5.0 N (1.2 lbf)
Fibre curl	≥4 m

Macrobend loss: The maximum attenuation with bending does not exceed the specified values with the following deployment conditions

Deployment condition	Wavelength	Induced attenuation
1 turn, 16 mm (0.6 inch) radius	1625 nm	≤0.05 dB
100 turns, 30 mm (1.18 inch) radius	1625 nm 1550 nm	≤0.10 dB ≤0.05 dB

## Environmental Characteristics

Temperature dependence Induced attenuation, -60°C to +85°C at 1550 nm & 1625 nm	≤0.05 dB/km
Temperature humidity cycling Induced attenuation -10°C to +85°C and 95% relative humidity at 1550 nm & 1625 nm	≤0.05 dB/km
High temperature and humidity aging 85°C at 85% RH, 30 days Induced attenuation at 1550 nm & 1625 nm	≤0.05 dB/km
Water immersion, 30 days, Induced attenuation due to water immersion at 23±2°C at 1550 nm & 1625 nm	≤0.05 dB/km
Accelerated aging (Temperature), 30 days Induced attenuation due to temperature aging at 85±2°C at 1550 nm & 1625 nm	≤0.05 dB/km

## Other Performance Characteristics\*

Effective group index of refraction	1.470 at 1550 nm
Attenuation in the wavelength region from 1525 - 1575 nm in reference to the attenuation at 1550 nm	≤0.02 dB/km
Point discontinuities at 1550 nm & 1625 nm	≤0.05 dB
Dynamic fatigue parameter (Nd)	≥20
Shipping Length: Standard length reel available up to	25.2 kms

\*Typical values

## Manufacturing Process

STL controls every stage of the manufacturing process so that quality is built in to every meter of fiber, rather than selected out at the end through testing. To ensure the accuracy and precision of the manufacturing process, STL routinely calibrates and recertifies process equipment and measurement benches against internationally traceable standards from NPL/NIST, and follow test methods compliant with EIA/TIA, CEI-IEC and ITU standards.

## International Standards

STL DOF-LITE™ (METRO) complies with ITU-T G.655 E.G.656 Optical Fiber Specification.

## Service USP's

- Complete range of optical fiber for terrestrial networks
- World-wide sales support
- Web-based order tracking & customer support
- Specialized technical support

## Disclaimer

STL's policy of continuous improvement may result in a change in specifications without prior notice. Any warranty of any nature relating to any STL product is only contained in the written agreement between STL and the direct purchaser of such product(s).

Issued: May 2019