



# STL OH-Lite 250 Fibre

## ITU-T G.652.D Single Mode Optical Fibre

### Product Description

STL OH-Lite 250 Single Mode Optical Fibre is a low water peak fibre where attenuation at 1380-1390 nm is less than attenuation at 1310 nm.

### Product Application

STL OH-Lite 250 Fibre is ideal for regional, metropolitan, and local access networks using CWDM.

### Product Benefits

STL OH-Lite 250 Fibre single mode fibre is designed for use over the entire 1260 nm to 1625 nm wavelength range. This gives it much more useable spectrum than conventional single mode fibre.

### Standard Compliance

STL routinely calibrates and recertifies process equipment and measurement benches against internationally traceable standards from NPL/NIST, and follow test methods compliant with EIA/TIA, CEI-IEC and ITU standards.

## Parameters

Optical Parameters		
<b>Attenuation Max. (dB/km)</b>		
1310 nm		≤ 0.34
1383 nm <sup>#</sup> #After hydrogen aging according to IEC-60793-2-50 regarding the B-652.D fibre category		≤ 0.34
1550 nm		≤ 0.20
1625 nm		≤ 0.23
<b>Macro bend loss (dB)</b>		
1 turn 16 mm radius	1550nm	≤ 0.5
100 turns 30 mm radius		≤ 0.05
100 turns 30 mm radius	1625nm	≤ 0.1
Mode Field Diameter (μm) at 1310 nm		9.1 ± 0.4
Mode Field Diameter (μm) at 1550 nm		10.3 ± 0.5
Cable cutoff wavelength (nm)		≤ 1260
Zero dispersion wavelength (nm)		1300 to 1324
Dispersion at 1550nm (ps/nm.km)		≤ 17.5
Zero Dispersion Slope (ps/nm <sup>2</sup> .km)		≤ 0.090
PMD LDV (ps/√ km)		≤ 0.2
Individual Fibre PMD* (ps/√ km) * Individual PMD values may change when cabled		≤ 0.2
Point of discontinuities 1310nm & 1550nm (dB)		≤ 0.05
<b>Geometrical Parameters</b>		
Cladding Diameter (μm)		125 ± 0.7
Core Clad Concentricity error (μm)		≤ 0.5
Cladding Non-circularity (%)		≤ 0.8
Coating Diameter (uncoloured) (μm)		242 ± 5
Coating Cladding Concentricity error (μm)		≤ 12
<b>Environmental Characteristics</b>		
Temperature dependence	-60°C to +85°C	≤ 0.05 (Induced Attenuation at 1310, 1550, 1625 nm (dB/km))
Temperature humidity cycling	-10°C to +85°C, 95% RH	
Water Immersion	30 days, 23 ± 2°C	
High temperature and humidity aging	30 days 85 ± 2°C, 85% RH	
Accelerated Aging (Temperature)	30 days, 85 ± 2°C	
<b>Mechanical Characteristics</b>		
Proof Testing		≥ 125 (kpsi) (0.86GN/m <sup>2</sup> ) (This is equivalent to 1.2% strain)
Fibre Curl (m)		≥ 4
<b>Performance Characteristics</b>		
Coating strip force		≥ 1.3 N (0.3 lbf) and ≤ 5.0 N (1.1 lbf)
Dynamic fatigue parameter (N <sub>d</sub> )		≥ 20
Effective group index of refraction (Typical Values)		1.4670 at 1310 nm 1.4675 at 1550 nm 1.4680 at 1625 nm
Attenuation in the wavelength region from 1285 - 1330 nm in reference to the attenuation at 1310 nm (dB/km)		≤ 0.03
Attenuation in the wavelength region from 1525 - 1575 nm in reference to the attenuation at 1550 nm (dB/km)		≤ 0.03

01/072023

**For additional information please contact your sales representative.**

You can also visit our website at [www.stl.tech](http://www.stl.tech)

The information given herein, including drawings, illustrations and schematics are intended for illustration purposes only and is believed to be reliable. However, STL makes no warranties to its accuracy or completeness and disclaims any liability in connection with its use. STL obligations shall be only set forth in STL standard terms and conditions of the sale and in no case, STL be liable for any incidental, indirect or consequential damages arising out of sale, resale, use or misuse of the product. Users of STL products should make their own evaluation to determine the suitability of such each product for the specific application.