



STL DOF-Lite 656 Fibre

ITU-T G.655.E/G.656 Single Mode Optical Fibre

Product Description

STL DOF-Lite 656 Single Mode Optical Fibre is a Non-Zero Dispersion Shifted Fibre (NZ-DSF).

Product Application

STL DOF-Lite 656 Fibre was designed for high data-rate, multi-wavelength long haul transmission. It is suitable for transmission in the conventional C-band (1530-1565 nm) and L-band (1565- 1625 nm).

Product Benefits

STL DOF-Lite 656 Fibre provides lower dispersion and dispersion slope which can be advantageous for metro networks. It is also compliant with current 100G/200G and beyond coherent technologies for long-haul networks.

Standard Compliance

STL routinely calibrates and recertifies process equipment and measurement benches against internationally traceable standards from NPL/NIST, and follow test methods compliant with EIA/TIA, CEI-IEC and ITU standards.

Parameters

Optical Parameters		
Attenuation Max. (dB/km)		
1550 nm		≤ 0.21
1625 nm		≤ 0.24
Macro bend loss (dB)		
100 turns 30 mm radius	1550nm	≤ 0.05
1 turn 16 mm radius	1625nm	≤ 0.05
100 turns 30 mm radius		≤ 0.1
Mode Field Diameter (μm) at 1550 nm		9.2 ± 0.5
Cable cutoff wavelength (nm)		≤ 1450
Dispersion at 1460 nm (ps/nm.km)		1.00 to 4.60
Dispersion at 1530 nm (ps/nm.km)		3.02 to 8.24
Dispersion at 1550nm (ps/nm.km)		3.60 to 9.28
Dispersion at 1565 nm (ps/nm.km)		3.80 to 10.13
Dispersion at 1625 nm (ps/nm.km)		4.58 to 13.43
PMD LDV (ps/√ km)		≤ 0.06
Individual Fibre PMD* (ps/√ km) * Individual PMD values may change when cabled		≤ 0.1
Point of discontinuities 1550nm & 1625nm (dB)		≤ 0.05
Geometrical Parameters		
Cladding Diameter (μm)		125 ± 0.7
Core Clad Concentricity error (μm)		≤ 0.5
Cladding Non-circularity (%)		≤ 0.8
Coating Diameter (uncoloured) (μm)		242 ± 5
Coating Cladding Concentricity error (μm)		≤ 12
Environmental Characteristics		
Temperature dependence	-60°C to +85°C	≤ 0.05 (Induced Attenuation at 1550, 1625 nm (dB/km))
Temperature humidity cycling	-10°C to +85°C, 95% RH	
Water Immersion	30 days, 23 ± 2°C	
High temperature and humidity aging	30 days 85 ± 2°C, 85% RH	
Accelerated Aging (Temperature)	30 days, 85 ± 2°C	
Mechanical Characteristics		
Proof Test Levels		≥ 100 kpsi (0.7GN/m ²). This is equivalent to 1% strain
Fibre Curl (m)		≥ 4
Performance Characteristics		
Coating strip force		≥ 1.3 N (0.3 lbf) and ≤ 5.0 N (1.1 lbf)
Dynamic fatigue parameter (N _d)		≥ 20
Effective group index of refraction (Typical Values)		1.470 at 1550 nm
Attenuation in the wavelength region from 1525 - 1575 nm in reference to the attenuation at 1550 nm (dB/km)		≤ 0.02

02/012024

For additional information please contact your sales representative.

You can also visit our website at www.stl.tech

The information given herein, including drawings, illustrations and schematics are intended for illustration purposes only and is believed to be reliable. However, STL makes no warranties to its accuracy or completeness and disclaims any liability in connection with its use. STL obligations shall be only set forth in STL standard terms and conditions of the sale and in no case, STL be liable for any incidental, indirect or consequential damages arising out of sale, resale, use or misuse of the product. Users of STL products should make their own evaluation to determine the suitability of such each product for the specific application.